

ATLANTIC NON DROP GREASE

(Bentone base Grease)

DESCRIPTION & APPLICATIONS

ATLANTIC NON DROP GREASE is a high-quality, extreme-pressure (EP), clay-thickened grease developed for the lubrication of industrial equipment operating under heavy loads and at high temperatures. It is particularly recommended for medium-to-large, low-speed bearings operating at very high temperatures where conventional soap-based greases typically fail to provide satisfactory lubrication.

ATLANTIC NON DROP GREASE is manufactured with high-quality, heavy paraffinic base oils and a non-soap, bentonite clay thickener. It is fortified with extreme-pressure and Anti wear additives to provide outstanding protection for bearings and moving parts exposed to heavy loads and high operating temperatures. It retains its consistency at high temperatures and has good water washout resistance and good storage stability.

PRODUCT BENEFITS

- Drying Ovens
- Kiln Cars
- Rolling and strip mills
- Aluminium, Cement, Glass and Rubber Plants
- Jaw Crushers
- Steel Mills

TYPICAL TECHNICAL PROPERTIES

Product code	12812G	12813G
Thickener Type	Bentonite	Bentonite
NLGI Classification	2	3
Texture	Smooth	Smooth
Color, Visual	Golden Brown	GoldenBrown
Dropping Point °C, ASTM D 566	Non-Melt	Non-Melt
Worked Penetration @25°C 60 strokes, ASTM D 217	265/295	220/250
Wheel Bearing leakage after 6hrs @ 110°C gms, ASTM D 1263	<2	<2
Water washout resistance %wt, ASTM D 1264	< 5	< 5
Copper Strip Corrosion for 24hrs @100°C, ASTM D 4048	1b	1b

ATL/PDS/G/027/0*, 10.08.20, Page 1/1
* supersedes all previous versions

Note: These characteristics are typical of current production. While future production will conform to Atlantic's specification, variations in these characteristics may occur.

Health and Safety: This lubricant, when used in accordance with our recommendations and for the application for which it is intended, does not constitute any special hazard A safety data file conforming to the requirements of current EC legislation is available from your local trade consultant.

Note: These characteristics are typical of current production. While future production will conform to Atlantic's specification, variations in these characteristics may occur.